

# Patent Abstracts of Japan

PUBLICATION NUMBER : 09132856

PUBLICATION DATE : 20-05-97

APPLICATION DATE : 06-11-95

APPLICATION NUMBER : 07286894

APPLICANT : OJI PAPER CO LTD;

INVENTOR : MIYOSHI TOMOJI;

INT.CL. : D04H 3/16 A61F 13/54 A61F 5/44 D04H 3/10 D04H 5/08

TITLE : STRETCHABLE SPUN-BONDED NONWOVEN FABRIC

ABSTRACT : PROBLEM TO BE SOLVED: To produce a stretchable spun-bonded nonwoven fabric which has excellent fabric hand, surface strength, readily stretchable in the transverse direction with an extremely small stress and suitably useful as a stretchable member in hygienic materials.

SOLUTION: This is a stretchable spun-bonded nonwoven fabric produced by the following processes. A thermoplastic resin is melt-extruded into continuous filaments, the group of continuous filament yarns are drawn with high-speed and high-pressure air from an ejector, taken up, opened, collected and accumulated on a yarn-collecting supporter to form a web. In this web, a continuous filament spun-bonded nonwoven fabric having a first regularly intermittent self-bonding region is formed in the longitudinal direction, and also a second regularly intermittent self-bonding region is formed by drawing nonwoven fabric so that the width ratio of the nonwoven fabric before and after drawing may become 100/90-100/50 by using hot rolls while keeping the width of the fabric after drawing. The spun-bonded nonwoven fabric consists of 2 sheets of the continuous filament spun-bonded nonwoven fabric having the first regularly intermittent self-bonding region. The stress at 50% elongation in the transverse direction is 50-200g, when it is measured with a stretchable spun-bonded nonwoven fabric of 25mm width.

COPYRIGHT: (C)1997,JPO